

Subcl 1. (Amended) An antireflective article comprising a substrate having an antireflective surface and an antisoiling coating that is at least partially cured thereon; wherein the antisoiling coating comprises a fluorinated siloxane prepared by applying a coating composition comprising at least one fluorinated silane having a number average molecular weight of at least about 1000 and the following formula:



(I)

Bl. wherein:  $R_f$  is a monovalent or divalent polyfluoropolyether group;  $R^1$  is a divalent alkylene group, arylene group, or combinations thereof, wherein  $R^1$  includes one or more substituents selected from the group consisting of heteroatoms and functional groups, and further wherein  $R^1$  optionally includes one or more halides;  $R^2$  is a  $C_1$ - $C_4$  [lower] alkyl group; Y is a halide, a  $C_1$ - $C_4$  [lower] alkoxy group, or a  $C_1$ - $C_4$  [lower] acyloxy group; x is 0 or 1; and y is 1 or 2.

2. The antireflective article of claim 1 wherein the antireflective surface comprises a metal oxide film having one or more metal oxides.
  3. The antireflective article of claim 2 wherein the antireflective surface comprises a vacuum deposited metal oxide film.
  4. The antireflective article of claim 3 wherein the antisoiling coating is at least about 15 Angstroms thick.
  5. The antireflective article of claim 4 wherein the antisoiling coating is no greater than about 150 Angstroms thick.
- B

Serial No.: 09/014,341

Filed: January 27, 1998

For: ANTISOILING COATINGS FOR ANTIREFLECTIVE SURFACES AND METHODS OF PREPARATION

6. The antireflective article of claim 1 which has a first surface antireflectivity that is different by less than about 0.5 percentage units from that of the same article without the antisoiling coating.

B2  
7. (Amended) The antireflective article of claim 1 wherein the coating is prepared by applying a coating composition comprising at least one fluorinated silane wherein each Y is a  $C_1-C_4$  [lower] alkoxy group.

8. The antireflective article of claim 1 wherein the coating is prepared by applying a coating composition comprising at least one fluorinated silane wherein  $R_f$  is a perfluoropolyether group.

Subc2  
B3  
~~9. (Amended) The antireflective article of claim 8 wherein the coating is prepared by applying a coating composition comprising at least one fluorinated silane wherein  $R_f$  is a perfluoropolyether group comprising perfluorinated repeating units selected from the group consisting of  $-(C_nF_{2n})-$ ,  $-(C_nF_{2n}O)-$ ,  $-(CF(Z))-$ ,  $-(CF(Z)O)-$ ,  $-(CF(Z)C_nF_{2n}O)-$ ,  $-(C_nF_{2n}CF(Z)O)-$ ,  $-(CF_2CF(Z)O)-$ , and combinations thereof, wherein n is about 1 to about 4 and Z is a perfluoroalkyl group, an oxygen-substituted perfluoroalkyl group, a perfluoroalkoxy group, or an oxygen-substituted perfluoroalkoxy group, each of which has about 1 to about 9 carbon atoms and 0 to about 4 oxygen atoms.~~

10. (Amended) The antireflective article of claim 1 wherein the coating is prepared by applying a coating composition comprising a fluorinated silane selected from the group consisting of  $XCF_2O(CF_2O)_m(C_2F_4O)_pCF_2X$ ,  $C_3F_7O(CF(CF_3)CF_2O)_pCF(CF_3)X$ ,  $XCF(CF_3)O(CF(CF_3)CF_2O)_pCF(CF_3)X$ ,  $XCF_2O(C_2F_4O)_pCF_2X$ ,  $CF_3O(C_2F_4O)_pCF_2X$ ,  $X(CF_2)_3O(C_4F_8O)_p(CF_2)_3X$ , and mixtures thereof, wherein:

-X is  $-R^1-SiY_{3-x}R^2_x$  as defined [above in formula] in claim 1 or a terminal group selected from the group consisting of  $(C_nF_{2n+1})-$ ,  $(C_nF_{2n+1}O)-$ ,  $(X'C_nF_{2n}O)-$ , and  $[(X'C_nF_{2n+1}O)-]$

$(X'C_nF_{2n})_m$ , wherein  $X'$  is H, Cl, or Br, with the proviso that at least one X group per molecule is a silane, and  $n$  is 1 or more;


an average value of  $m$  is within a range of about 1 to about 50; and

an average value of  $p$  is within a range of about 4 to about 40.

11. The antireflective article of claim 1 wherein the antisoiling coating composition further includes an alkyl perfluoroalkyl ether.

12. The antireflective article of claim 1 wherein  $R^1$  includes about 2 to about 16 carbon atoms.

13. (Amended) An antisoiling coating composition comprising at least one fluorinated silane having a number average molecular weight of at least about 1000 and an alkyl perfluoroalkyl ether, wherein the fluorinated silane has the following formula:



(I)

wherein:  $R_f$  is a monovalent or divalent polyfluoropolyether group;  $R^1$  is a divalent alkylene group, arylene group, or combinations thereof, wherein  $R^1$  optionally includes one or more substituents selected from the group consisting of heteroatoms, functional groups, and halides;  $R^2$  is a  $C_1$ - $C_4$  [lower] alkyl group;  $Y$  is a halide, a  $C_1$ - $C_4$  [lower] alkoxy group, or a  $C_1$ - $C_4$  [lower] acyloxy group;  $x$  is 0 or 1; and  $y$  is 1 or 2.

14. (Amended) The antisoiling composition of claim 13 wherein  $R_f$  has an approximate average structure selected from the group consisting of  $-CF_2O(CF_2O)_m(C_2F_4O)_pCF_2-$ ,

Serial No.: 09/014,341

Filed: January 27, 1998

For: ANTISOILING COATINGS FOR ANTIREFLECTIVE SURFACES AND METHODS OF PREPARATION

$-\text{CF}(\text{CF}_3)\text{O}(\text{CF}(\text{CF}_3)\text{CF}_2\text{O})_p\text{CF}(\text{CF}_3)-$ ,  $-\text{CF}_2\text{O}(\text{C}_2\text{F}_4\text{O})_p\text{CF}_2-$ , and  $-(\text{CF}_2)_3\text{O}(\text{C}_4\text{F}_8\text{O})_p(\text{CF}_2)_3-$ , wherein  $m$  has an average value of 0 to about 50, and  $p$  has an average value of 0 to about 50, with the proviso that both  $m$  and  $p$  cannot be 0 in the same group.

15. (Amended) A method of applying an antisoiling coating to a substrate having an antireflective surface, the method comprising treating the antireflective surface with a coating composition comprising at least one fluorinated silane having a number average molecular weight of at least about 1000 and the following formula:



(I)

wherein:  $\text{R}_f$  is a monovalent or divalent polyfluoropolyether group;  $\text{R}^1$  is a divalent alkylene group, arylene group, or combinations thereof, wherein  $\text{R}^1$  includes one or more substituents selected from the group consisting of heteroatoms and functional groups, and further wherein  $\text{R}^1$  optionally includes one or more halides;  $\text{R}^2$  is a  $\text{C}_1$ - $\text{C}_4$  [lower] alkyl group;  $\text{Y}$  is a halide, a  $\text{C}_1$ - $\text{C}_4$  [lower] alkoxy group, or a  $\text{C}_1$ - $\text{C}_4$  [lower] acyloxy group;  $x$  is 0 or 1; and  $y$  is 1 or 2.

16. (Amended) The method of claim 15 wherein the coating composition further comprises a nonchlorinated solvent selected from the group consisting of a fluorinated alkane, an alkyl perfluoroalkyl ether, and mixtures thereof.

17. (Amended) The method of claim 15 wherein the coating is prepared by applying a coating composition comprising a fluorinated silane selected from the group consisting of  $\text{XCF}_2\text{O}(\text{CF}_2\text{O})_m(\text{C}_2\text{F}_4\text{O})_p\text{CF}_2\text{X}$ ,  $\text{C}_3\text{F}_7\text{O}(\text{CF}(\text{CF}_3)\text{CF}_2\text{O})_p\text{CF}(\text{CF}_3)\text{X}$ ,  $\text{XCF}(\text{CF}_3)\text{O}(\text{CF}(\text{CF}_3)\text{CF}_2\text{O})_p\text{CF}(\text{CF}_3)\text{X}$ ,  $\text{XCF}_2\text{O}(\text{C}_2\text{F}_4\text{O})_p\text{CF}_2\text{X}$ ,  $\text{CF}_3\text{O}(\text{C}_2\text{F}_4\text{O})_p\text{CF}_2\text{X}$ ,  $\text{X}(\text{CF}_2)_3\text{O}(\text{C}_4\text{F}_8\text{O})_p(\text{CF}_2)_3\text{X}$ , and mixtures thereof, wherein:

$-\text{X}$  is  $-\text{R}^1-\text{SiY}_{3-x}\text{R}^2_x$  as defined above in [formula I] claim 15 or a terminal group selected from the group consisting of  $(\text{C}_n\text{F}_{2n+1})-$ ,  $(\text{C}_n\text{F}_{2n+1}\text{O})-$ ,  $(\text{X}'\text{C}_n\text{F}_{2n})-$ , and  $[(\text{X}'\text{C}_n\text{F}_{2n+1}\text{O})-, (\text{X}'\text{C}_n\text{F}_{2n})-,$

wherein X' is H, Cl, or Br, with the proviso that at least one X group per molecule is a silane, and  
n is 1 or more;

an average value of m is within a range of about 1 to about 50; and

an average value of p is within a range of about 4 to about 40.

18. The method of claim 15 wherein the antisoiling coating formed is at least about 15 Angstroms thick.

19. The method of claim 18 wherein the antisoiling coating formed is no greater than about 150 Angstroms thick.

20. The method of claim 15 wherein the step of treating comprises coating the composition at room temperature followed by heating the coated composition at a temperature of at least about 100°C.

21. The method of claim 15 wherein the coating composition comprising the fluorinated silane comprises less than about 2.0 weight percent of the fluorinated silane.

22. The method of claim 15 wherein the step of treating comprises continuously roll coating the composition onto the substrate.

23. The method of claim 22 wherein the step of gravure coating comprises feeding the coating composition to a doctor blade, transferring the coating composition from the doctor blade to a gravure roll, and applying the coating composition to the antireflective surface of the substrate from the gravure roll.

Serial No.: 09/014,341

Filed: January 27, 1998

For: ANTISOILING COATINGS FOR ANTIREFLECTIVE SURFACES AND METHODS OF PREPARATION

24. The method of claim 23 wherein the step of coating the antisoiling coating composition further comprises applying a soft roll to a surface opposing the antireflective surface of the transparent substrate.

25. The method of claim 22 wherein the antisoiling coating composition further comprises a nonchlorinated solvent.

B5 ~~26~~<sup>26</sup>. (Amended) The method of claim ~~25~~<sup>26</sup> wherein the solvent is selected from the group consisting of a fluorinated alkane, an alkyl perfluoroalkyl ether, and mixtures thereof.

27. The method of claim 26 wherein the solvent is an alkyl perfluoroalkyl ether.

28. An antireflective article made by the method of claim 22.

~~32~~<sup>31</sup>. (Amended) An antireflective article comprising:

a transparent substrate having a first surface and a second surface;

an antireflective coating on at least a portion of the first surface; and

B6 an antisoiling coating disposed on the antireflective coating, wherein the antisoiling coating comprises [comprising] siloxane groups and polyfluoropolyether segments covalently bonded to silicon via organic linking groups, wherein the polyfluoropolyether segments have a molecular weight of at least about 1000 and the organic linking groups include nitrogen atoms.

B7 ~~32~~<sup>31</sup>. (Amended) The antireflective article of claim ~~29~~<sup>31</sup> [30] wherein the antisoiling coating has a fluorine atom to nitrogen atom ratio of about 25 to about 150.

Sub C 32. (Amended) The antireflective article of claim 29 wherein the antisoiling coating comprises a fluorinated siloxane prepared by applying a coating composition comprising at least one fluorinated silane having a number average molecular weight of at least about 1000 and the following formula:



(I)

B7  
C 32  
wherein:  $R_f$  is a monovalent or divalent polyfluoropolyether group;  $R^1$  is a divalent alkylene group, arylene group, or combinations thereof, wherein  $R^1$  optionally includes one or more substituents selected from the group consisting of heteroatoms, functional groups, and halides;  $R^2$  is a  $C_1$ - $C_4$  [lower] alkyl group; Y is a halide, a  $C_1$ - $C_4$  [lower] alkoxy group, or a  $C_1$ - $C_4$  [lower] acyloxy group; x is 0 or 1; and y is 1 or 2.

33. The antireflective article of claim 32 wherein the  $R^1$  group contains heteroatoms or functional groups and is optionally substituted with halides.

34. The antireflective article of claim 33 wherein  $R^1$  is a divalent hydrocarbon containing at least one functional group.

35. The antireflective article of claim 29 wherein the transparent substrate comprises a flexible organic polymeric material.

36. The antireflective article of claim 35 further comprising an adhesion-enhancing coating disposed between the flexible organic polymeric substrate and the antireflective coating.

37. The antireflective article of claim 36 wherein the antireflective coating comprises a metal oxide film having one or more metal oxides.

B

38. The antireflective article of claim 37 wherein the antireflective surface comprises a vacuum deposited metal oxide film.

~~38~~ 39. (Amended) [The antireflective article of claim ~~38~~ further including] An antireflective article comprising:

a transparent substrate comprising a flexible organic polymeric material having a first surface and a second surface;

an antireflective coating on at least a portion of the first surface;

a layer of a pressure sensitive adhesive disposed on the second surface of the substrate;

and

an antisoiling coating on at least a portion of the antireflective coating, wherein the antisoiling coating comprises siloxane groups and polyfluoropolyether segments covalently bonded to silicon via organic linking groups, wherein the polyfluoropolyether segments have a molecular weight of at least about 1000.

Sub 5  
B9  
40. (New) An antireflective article comprising a substrate having an antireflective surface and an antisoiling coating that is at least partially cured thereon; wherein the antisoiling coating comprises a fluorinated siloxane prepared by applying a coating composition comprising at least one fluorinated silane having a number average molecular weight of at least about 1000 and the following formula:



(I)

wherein:  $R_f$  is a monovalent or divalent polyfluoropolyether group;  $R^1$  is a divalent alkylene groups, arylene group, or combinations thereof, wherein  $R^1$  optionally includes one or more substituents selected from the group consisting of heteroatoms, functional groups, and halides;  $R^2$  is a  $C_1$ - $C_4$  alkyl group;  $Y$  is a halide, a  $C_1$ - $C_4$  alkoxy group, or a  $C_1$ - $C_4$  acyloxy group;  $x$  is 0 or 1;



Subst  
cond  
and y is 1 or 2 and further wherein the antisoiling coating composition includes an alkyl perfluoroalkyl ether.

41. (New) An antireflective article comprising a substrate having an antireflective surface and an antisoiling coating that is at least partially cured thereon; wherein the antisoiling coating comprises a fluorinated siloxane prepared by applying a coating composition comprising at least one fluorinated silane having a number average molecular weight of at least about 1000 and the following formula:



(I)

B9  
Cond.  
wherein:  $R_f$  is a divalent polyfluoropolyether group;  $R^1$  is a divalent alkylene group, arylene group, or combinations thereof, wherein  $R^1$  optionally includes one or more substituents selected from the group consisting of heteroatoms, functional groups, and halides;  $R^2$  is a  $C_1$ - $C_4$  alkyl group; Y is a halide, a  $C_1$ - $C_4$  alkoxy group, or a  $C_1$ - $C_4$  acyloxy group; x is 0 or 1; and y is 2.

42. (New) A method of applying an antisoiling coating to a substrate having an antireflective surface, the method comprising treating the antireflective surface with a coating composition comprising at least one fluorinated silane having a number average molecular weight of at least about 1000 and the following formula:



(I)

wherein:  $R_f$  is a divalent polyfluoropolyether group;  $R^1$  is a divalent alkylene group, arylene group, or combinations thereof, wherein  $R^1$  optionally includes one or more substituents selected from the group consisting of heteroatoms, functional groups, and halides;  $R^2$  is a  $C_1$ - $C_4$  alkyl group; Y is a halide, a  $C_1$ - $C_4$  alkoxy group, or a  $C_1$ - $C_4$  acyloxy group; x is 0 or 1; and y is 2.

B

43. (New) An antireflective article comprising a substrate having an antireflective surface and an antisoiling coating that is at least partially cured thereon; wherein the antisoiling coating comprises a fluorinated siloxane prepared by applying at least one fluorinated silane having a number average molecular weight of at least about 1000 and the following formula:



(I)

wherein:  $R_f$  is a monovalent or divalent polyfluoropolyether group;  $R^1$  is a divalent alkylene group, arylene group, or combinations thereof, wherein  $R^1$  includes one or more substituents selected from the group consisting of heteroatoms and functional groups, and further wherein  $R^1$  optionally includes one or more halides;  $R^2$  is a  $C_1$ - $C_4$  alkyl group;  $Y$  is a halide, a  $C_1$ - $C_4$  alkoxy group, or a  $C_1$ - $C_4$  acyloxy group;  $x$  is 0 or 1; and  $y$  is 1 or 2.

44. (New) A method of applying an antisoiling coating to a substrate having an antireflective surface, the method comprising treating the antireflective surface with at least one fluorinated silane having a number average molecular weight of at least about 1000 and the following formula:



(I)

wherein:  $R_f$  is a monovalent or divalent polyfluoropolyether group;  $R^1$  is a divalent alkylene group, arylene group, or combinations thereof, wherein  $R^1$  includes one or more substituents selected from the group consisting of heteroatoms and functional groups, and further wherein  $R^1$  optionally includes one or more halides;  $R^2$  is a  $C_1$ - $C_4$  alkyl group;  $Y$  is a halide, a  $C_1$ - $C_4$  alkoxy group, or a  $C_1$ - $C_4$  acyloxy group;  $x$  is 0 or 1; and  $y$  is 1 or 2.